

PATENT ABSTRACTS OF JAPAN

(11)Publication number : **06-049159**
 (43)Date of publication of application : **22.02.1994**

(51)Int.Cl. **C08G 8/10**
F16D 69/02

(21)Application number : **04-202499** (71)Applicant : **SUMITOMO DUREZ CO LTD**
 (22)Date of filing : **29.07.1992** (72)Inventor : **KOBAYASHI TAKASHI**
NOGUCHI KENICHI

(54) NOVOLAC PHENOLIC RESIN COMPOSITION FOR FRICTION MATERIAL

(57)Abstract:

PURPOSE: To obtain a novolac phenolic resin composition excellent in frictional properties, workability and environmental protection by specifying the contents of mononuclear and binuclear components in the novolac phenolic resin.

CONSTITUTION: The composition comprises a novolac phenolic resin obtained by using a phenol and a formaldehyde as the essential components and having a mononuclear component content of 1wt.% or below and a binuclear component content of 2wt.% or below. This resin desirably has a number-average molecular weight of 300-800 and a number-average molecular weight to weight-average molecular weight ratio of 1.0-2.0.